

[Clear Form](#)

Michigan Department
Of Transportation
1903B (05/15)

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

File 208

CONTROL SECTION STU 82000	JOB NUMBER 205935A	PROJECT LOCATION HMA Resurfacing 20+ Various Locations	MIX DESIGN NO 19MD140	MIXTURE TYPE 5E3	DATE SAMPLED 11/09/19	DATE TESTED 11/18/19
CONTRACTOR AJAX Paving Industries, Inc.			PLANT NUMBER 20-10	PLANT LOCATION Warren (Sherwood)		SUBLOT SIZE AM
PROJECT ENGINEER Richard T. Doherty - City of Detroit Engineering		NAME OF TESTER (Please Print) Brian Gondek - Somat Engineering, Inc.		QUALIFICATION NO. 0383-0421	LOT NUMBER 4	SUB LOT NUMBER 1
Gb 1.029	Gsb 2.696	Gse 2.763	NAME OF TESTER (Signature) Brian Gondek Digitally signed by Brian Gondek DN: cn=Brian Gondek, o=Somat Engineering Inc., ou=Laboratory Supervisor, email=bgondek@somateng.com, c=US Date: 2019.11.26 13:51:17 -0500		FORM 1911 DATE 09/30/19	SUBLOT RANDOM TONS 50.16
					ACCUMULATED TONS 592.13	

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF*	MDOT DIFF. CONTR*	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF*	MDOT DIFF. CONTR*	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	+/- 5.0	ASPHALT %	6.15	6.10		-0.05	6.10	-0.3 / +0.4
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	+/- 5.0	Gmm	2.504					
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	+/- 5.0	Gmb @ N DESIGN	2.416					
P ½" (12.5 mm)	100.00	100.00		0.00	100.00	+/- 5.0	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	99.50	99.04		-0.46	99.04	+/- 5.0	VMA	15.90					
P No. 4 (4.75 mm)	83.50	83.07		-0.43	83.07	+/- 5.0	VFA	77.99					
P No. 8 (2.36 mm)	62.20	63.96		1.76	63.96	+/- 5.0	F/A RATIO	1.17					
P No. 16 (1.18 mm)	46.40	50.71		4.31	50.71			GRADE		CERTIFIED SUPPLIER/LOCATION/CERT#			% ADD
P No. 30 (600 µm)	34.80	36.31		1.51	36.31	+/- 4.0	ASPHALT BINDER	PG 58-28		Ajax Terminal/Detroit/2500			4.54
P No. 50 (300 µm)	18.20	19.02		0.82	19.02		Gmb WEIGHTS/COMPACTION TEMPERATURE 255 degrees F						
P No. 100 (150 µm)	10.20	9.26		-0.94	9.26								
P No. 200 (75 µm)	6.20	7.00		0.80	7.00	+/- 1.0	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.7	96.7		-1.0	96.7	< 10%							
CRUSH – 2 FACE													

REMARKS Sample Load: 12, Time: 12:10 PM, Location: McClellan just past Graves Left Lane Field Sampled by: Andrew Patterson

Within RANGE 1 tolerance limits for Top Course (12SP-501J-05 dated 07-05-16)

*CIRCLE TEST RESULTS OUT OF TOLERANCE