

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION 82000	JOB NUMBER 205935A/207914A	PROJECT LOCATION On Various Routes	MIX DESIGN NO 19MD411	MIXTURE TYPE 4E3	DATE SAMPLED 05/06/20	DATE TESTED 05/13/20
CONTRACTOR AJAX Paving Industries, Inc.			PLANT NUMBER 020-10	PLANT LOCATION Warren		SUBLOT SIZE
PROJECT ENGINEER Richard T. Doherty		NAME OF TESTER (Please Print) Brian Gondek		QUALIFICATION NO. 383-0421	LOT NUMBER 1	SUB LOT NUMBER 2 PM
Gb 1.029	Gsb 2.707	Gse 2.752	NAME OF TESTER (Signature) Brian J. Gondek Jun 25 2020 9:21 AM		FORM 1911 DATE 04/14/20	SUBLOT RANDOM TONS 431.00
ACCUMULATED TONS						

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5	ASPHALT %	5.15	5.18		0.03	5.18	+0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5	Gmm	2.534	2.537		0.003	2.537	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5	Gmb @ N DESIGN	2.445					
P ½" (12.5 mm)	99.40	95.90		-3.50	95.90	5	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	84.00	85.65		1.65	85.65	5	VMA	14.34					
P No. 4 (4.75 mm)	61.60	61.67		0.07	61.67	5	VFA	75.58					
P No. 8 (2.36 mm)	45.60	45.60		0.00	45.60	5	F/A RATIO	1.21					
P No. 16 (1.18 mm)	34.00	34.81		0.81	34.81		Gse						
P No. 30 (600 µm)	26.50	24.54		-1.96	24.54	4		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	14.20	13.37		-0.83	13.37		ASPHALT BINDER			Ajax Asphalt Terminal			3.79
P No. 100 (150 µm)	8.50	6.85		-1.65	6.85		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	5.50	4.72		-0.78	4.72	1	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.0	98.2		1.2	98.2	10							
CRUSH – 2 FACE													

REMARKS Sampled at M-10 and Lafayette at 1:20 PM

* CIRCLE TEST RESULTS OUT OF TOLERANCE