

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION 82000		JOB NUMBER 205935A/207914A		PROJECT LOCATION On Various Routes		MIX DESIGN NO 19MD411		MIXTURE TYPE 4E3		DATE SAMPLED 05/13/20		DATE TESTED 05/16/20			
CONTRACTOR AJAX Paving Industries, Inc.						PLANT NUMBER 020-10		PLANT LOCATION Warren				SUBLOT SIZE			
PROJECT ENGINEER Richard T. Doherty				NAME OF TESTER <i>(Please Print)</i> Brian Gondek				QUALIFICATION NO. 383-0421		LOT NUMBER 4		SUB LOT NUMBER 2 PM			
Gb 1.029		Gsb 2.707		Gse 2.752		NAME OF TESTER <i>(Signature)</i> Brian J. Gondek Brian J. Gondek Jun 25 2020 9:30 AM				FORM 1911 DATE 04/14/20		SUBLOT RANDOM TONS 1,151.00		ACCUMULATED TONS	

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5	ASPHALT %	5.15	4.99		-0.16	4.99	+0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5	Gmm	2.534	2.530		-0.004	2.530	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5	Gmb @ N DESIGN	2.445					
P ½" (12.5 mm)	99.40	94.71		-4.69	94.71	5	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	84.00	83.51		-0.49	83.51	5	VMA	14.34					
P No. 4 (4.75 mm)	61.60	61.95		0.35	61.95	5	VFA	75.58					
P No. 8 (2.36 mm)	45.60	45.93		0.33	45.93	5	F/A RATIO	1.21					
P No. 16 (1.18 mm)	34.00	36.69		2.69	36.69		Gse						
P No. 30 (600 µm)	26.50	27.15		0.65	27.15	4		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	14.20	14.78		0.58	14.78		ASPHALT BINDER			Ajax Asphalt Terminal			3.79
P No. 100 (150 µm)	8.50	8.70		0.20	8.70		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	5.50	6.19		0.69	6.19	1	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.0	97.5		0.5	97.5	10							
CRUSH – 2 FACE													

REMARKS Sampled on M-10 Service Drive at 2:45 PM

* CIRCLE TEST RESULTS OUT OF TOLERANCE