

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION 82000		JOB NUMBER 205935A/207914A		PROJECT LOCATION On Various Routes		MIX DESIGN NO 19MD411		MIXTURE TYPE 4E3		DATE SAMPLED 05/20/20		DATE TESTED 05/26/20	
CONTRACTOR AJAX Paving Industries, Inc.						PLANT NUMBER 020-10		PLANT LOCATION Warren				SUBLOT SIZE	
PROJECT ENGINEER Richard T. Doherty				NAME OF TESTER (Please Print) Brian Gondek				QUALIFICATION NO. 383-0421		LOT NUMBER 5		SUB LOT NUMBER 2 PM	
Gb 1.029		Gsb 2.707		Gse 2.752		NAME OF TESTER (Signature) Brian J. Gondek Jun 25 2020 9:31 AM				FORM 1911 DATE 04/14/20		SUBLOT RANDOM TONS 352.00	
ACCUMULATED TONS													

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5	ASPHALT %	5.15	4.83		-0.32	4.83	+0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5	Gmm	2.534	2.531		-0.003	2.531	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5	Gmb @ N DESIGN	2.445					
P ½" (12.5 mm)	99.40	97.20		-2.20	97.20	5	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	84.00	85.15		1.15	85.15	5	VMA	14.34					
P No. 4 (4.75 mm)	61.60	60.14		-1.46	60.14	5	VFA	75.58					
P No. 8 (2.36 mm)	45.60	44.87		-0.73	44.87	5	F/A RATIO	1.21					
P No. 16 (1.18 mm)	34.00	35.64		1.64	35.64		Gse						
P No. 30 (600 µm)	26.50	25.29		-1.21	25.29	4		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	14.20	14.01		-0.19	14.01		ASPHALT BINDER			Ajax Asphalt Terminal			3.79
P No. 100 (150 µm)	8.50	7.95		-0.55	7.95		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	5.50	6.00		0.50	6.00	1	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.0	97.1		0.1	97.1	10							
CRUSH – 2 FACE													

REMARKS Sampled on Spinoza and Joy at 2:15 PM

* CIRCLE TEST RESULTS OUT OF TOLERANCE