

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION 82000	JOB NUMBER 205935A/207914A	PROJECT LOCATION On Various Routes	MIX DESIGN NO 19MD411	MIXTURE TYPE 4E3	DATE SAMPLED 05/28/20	DATE TESTED 06/04/20
CONTRACTOR AJAX Paving Industries, Inc.			PLANT NUMBER 020-10	PLANT LOCATION Warren		SUBLOT SIZE
PROJECT ENGINEER Richard T. Doherty		NAME OF TESTER <i>(Please Print)</i> Brian Gondek		QUALIFICATION NO. 383-0421	LOT NUMBER 8	SUB LOT NUMBER 2 PM
Gb 1.029	Gsb 2.707	Gse 2.752	NAME OF TESTER <i>(Signature)</i> Brian J. Gondek Jun 25 2020 9:37 AM		FORM 1911 DATE 04/14/20	SUBLOT RANDOM TONS 599.00
ACCUMULATED TONS						

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5	ASPHALT %	5.15	5.10		-0.05	5.10	+0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5	Gmm	2.534	2.531		-0.003	2.531	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5	Gmb @ N DESIGN	2.445					
P ½" (12.5 mm)	99.40	97.04		-2.36	97.04	5	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	84.00	87.48		3.48	87.48	5	VMA	14.34					
P No. 4 (4.75 mm)	61.60	62.69		1.09	62.69	5	VFA	75.58					
P No. 8 (2.36 mm)	45.60	47.55		1.95	47.55	5	F/A RATIO	1.21					
P No. 16 (1.18 mm)	34.00	37.05		3.05	37.05		Gse						
P No. 30 (600 µm)	26.50	26.17		-0.33	26.17	4		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	14.20	15.38		1.18	15.38		ASPHALT BINDER			Ajax Asphalt Terminal			3.80
P No. 100 (150 µm)	8.50	8.76		0.26	8.76		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	5.50	6.37		0.87	6.37	1	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.0	96.9		-0.1	96.9	10							
CRUSH – 2 FACE													

REMARKS Sampled on Burt and Davison At 12:15 PM

* CIRCLE TEST RESULTS OUT OF TOLERANCE