

# REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

|                                            |                               |                                               |                                                                      |                               |                            |                                |
|--------------------------------------------|-------------------------------|-----------------------------------------------|----------------------------------------------------------------------|-------------------------------|----------------------------|--------------------------------|
| CONTROL SECTION<br>82000                   | JOB NUMBER<br>205935A/207914A | PROJECT LOCATION<br>On Various Routes         | MIX DESIGN NO<br>19MD411                                             | MIXTURE TYPE<br>4E3           | DATE SAMPLED<br>05/30/20   | DATE TESTED<br>06/05/20        |
| CONTRACTOR<br>AJAX Paving Industries, Inc. |                               |                                               | PLANT NUMBER<br>020-10                                               | PLANT LOCATION<br>Warren      |                            | SUBLOT SIZE                    |
| PROJECT ENGINEER<br>Richard T. Doherty     |                               | NAME OF TESTER (Please Print)<br>Brian Gondek |                                                                      | QUALIFICATION NO.<br>383-0421 | LOT NUMBER<br>9            | SUB LOT NUMBER<br>2 PM         |
| Gb<br>1.029                                | Gsb<br>2.707                  | Gse<br>2.752                                  | NAME OF TESTER (Signature)<br>Brian J. Gondek<br>Jun 25 2020 9:39 AM |                               | FORM 1911 DATE<br>04/14/20 | SUBLOT RANDOM TONS<br>1,394.00 |
| ACCUMULATED TONS                           |                               |                                               |                                                                      |                               |                            |                                |

| TEST RESULTS       |        |        |       |                        |                          |     | TEST RESULTS                                                                     |       |       |                                     |                        |                          |             |
|--------------------|--------|--------|-------|------------------------|--------------------------|-----|----------------------------------------------------------------------------------|-------|-------|-------------------------------------|------------------------|--------------------------|-------------|
|                    | JMF    | MDOT   | CONTR | MDOT<br>DIFF.<br>JMF * | MDOT<br>DIFF.<br>CONTR * | TOL |                                                                                  | JMF   | MDOT  | CONTR                               | MDOT<br>DIFF.<br>JMF * | MDOT<br>DIFF.<br>CONTR * | TOL         |
| P 1-½" (37.5 mm)   | 100.00 | 100.00 |       | 0.00                   | 100.00                   | 5   | ASPHALT %                                                                        | 5.15  | 5.18  |                                     | 0.03                   | 5.18                     | +0.40/-0.30 |
| P 1" (25.0 mm)     | 100.00 | 100.00 |       | 0.00                   | 100.00                   | 5   | Gmm                                                                              | 2.534 | 2.531 |                                     | -0.003                 | 2.531                    |             |
| P ¾" (19.0 mm)     | 100.00 | 100.00 |       | 0.00                   | 100.00                   | 5   | Gmb @ N DESIGN                                                                   | 2.445 |       |                                     |                        |                          |             |
| P ½" (12.5 mm)     | 99.40  | 97.32  |       | -2.08                  | 97.32                    | 5   | AIR VOIDS                                                                        | 3.50  |       |                                     |                        |                          |             |
| P 3/8" (9.5 mm)    | 84.00  | 85.85  |       | 1.85                   | 85.85                    | 5   | VMA                                                                              | 14.34 |       |                                     |                        |                          |             |
| P No. 4 (4.75 mm)  | 61.60  | 64.97  |       | 3.37                   | 64.97                    | 5   | VFA                                                                              | 75.58 |       |                                     |                        |                          |             |
| P No. 8 (2.36 mm)  | 45.60  | 47.98  |       | 2.38                   | 47.98                    | 5   | F/A RATIO                                                                        | 1.21  |       |                                     |                        |                          |             |
| P No. 16 (1.18 mm) | 34.00  | 37.59  |       | 3.59                   | 37.59                    |     | Gse                                                                              |       |       |                                     |                        |                          |             |
| P No. 30 (600 µm)  | 26.50  | 25.62  |       | -0.88                  | 25.62                    | 4   |                                                                                  | GRADE |       | CERTIFIED SUPPLIER / LOCATION/CERT# |                        |                          | % ADD       |
| P No. 50 (300 µm)  | 14.20  | 15.01  |       | 0.81                   | 15.01                    |     | ASPHALT BINDER                                                                   |       |       | Ajax Asphalt Terminal               |                        |                          | 3.80        |
| P No. 100 (150 µm) | 8.50   | 8.63   |       | 0.13                   | 8.63                     |     | Gmb WEIGHTS/COMPACTION TEMPERATURE                                               |       |       |                                     |                        |                          |             |
| P No. 200 (75 µm)  | 5.50   | 6.34   |       | 0.84                   | 6.34                     | 1   | NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %) |       |       |                                     |                        |                          |             |
| CRUSH – 1 FACE     | 97.0   | 97.8   |       | 0.8                    | 97.8                     | 10  |                                                                                  |       |       |                                     |                        |                          |             |
| CRUSH – 2 FACE     |        |        |       |                        |                          |     |                                                                                  |       |       |                                     |                        |                          |             |

REMARKS Sampled on Burt and Capitol

\* CIRCLE TEST RESULTS OUT OF TOLERANCE