

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION 82000	JOB NUMBER 205935A/207914A	PROJECT LOCATION On Various Routes	MIX DESIGN NO 19MD411	MIXTURE TYPE 4E3	DATE SAMPLED 06/04/20	DATE TESTED 06/29/20
CONTRACTOR AJAX Paving Industries, Inc.			PLANT NUMBER 020-10	PLANT LOCATION Warren		SUBLOT SIZE
PROJECT ENGINEER Richard T. Doherty		NAME OF TESTER (Please Print) Brian Gondek		QUALIFICATION NO. 383-0421	LOT NUMBER 12	SUB LOT NUMBER 2 PM
Gb 1.029	Gsb 2.707	Gse 2.752	NAME OF TESTER (Signature) Brian J. Gondek Aug 6 2020 8:04 AM		FORM 1911 DATE 04/14/20	SUBLOT RANDOM TONS 1,359.00
ACCUMULATED TONS						

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5	ASPHALT %	5.15	5.30		0.15	5.30	+0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5	Gmm	2.534	2.531		-0.003	2.531	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5	Gmb @ N DESIGN	2.445					
P ½" (12.5 mm)	99.40	96.06		-3.34	96.06	5	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	84.00	86.20		2.20	86.20	5	VMA	14.34					
P No. 4 (4.75 mm)	61.60	63.91		2.31	63.91	5	VFA	75.58					
P No. 8 (2.36 mm)	45.60	47.76		2.16	47.76	5	F/A RATIO	1.21					
P No. 16 (1.18 mm)	34.00	37.57		3.57	37.57		Gse						
P No. 30 (600 µm)	26.50	27.76		1.26	27.76	4		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	14.20	14.74		0.54	14.74		ASPHALT BINDER			Ajax Asphalt Terminal			3.80
P No. 100 (150 µm)	8.50	7.73		-0.77	7.73		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	5.50	5.42		-0.08	5.42	1	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.0	97.8		0.8	97.8	10							
CRUSH – 2 FACE													

REMARKS sampled at Jos Camp. & Halleck @ 2:45PM

* CIRCLE TEST RESULTS OUT OF TOLERANCE