

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION 82000	JOB NUMBER 205935A	PROJECT LOCATION On Various Routes	MIX DESIGN NO 19MD140	MIXTURE TYPE 5E3	DATE SAMPLED 06/08/20	DATE TESTED 07/03/20
CONTRACTOR AJAX Paving Industries, Inc.			PLANT NUMBER 020-10	PLANT LOCATION Warren		SUBLOT SIZE
PROJECT ENGINEER Richard T. Doherty			NAME OF TESTER <i>(Please Print)</i> Brian Gondek		QUALIFICATION NO. 383-0421	LOT NUMBER 1
						SUB LOT NUMBER 2 PM
Gb 1.029	Gsb 2.696	Gse 2.763	NAME OF TESTER <i>(Signature)</i> Brian J. Gondek Aug 6 2020 8:35 AM		FORM 1911 DATE 04/14/20	SUBLOT RANDOM TONS 352.00
ACCUMULATED TONS						

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5.0	ASPHALT %	6.15	6.03		-0.12	6.03	+0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmm	2.504	2.500		-0.004	2.500	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmb @ N DESIGN	2.416					
P ½" (12.5 mm)	100.00	98.85		-1.15	98.85	5.0	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	99.50	97.42		-2.08	97.42	5.0	VMA	15.90					
P No. 4 (4.75 mm)	83.50	78.96		-4.54	78.96	5.0	VFA	77.99					
P No. 8 (2.36 mm)	62.20	62.42		0.22	62.42	5.0	F/A RATIO	1.17					
P No. 16 (1.18 mm)	46.40	51.34		4.94	51.34		Gse						
P No. 30 (600 µm)	34.80	36.67		1.87	36.67	4.0		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	18.20	19.13		0.93	19.13		ASPHALT BINDER	PG 58-28		Ajax Asphalt Terinal Detroit 2500			4.54
P No. 100 (150 µm)	10.20	9.33		-0.87	9.33		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	6.20	6.67		0.47	6.67	1.0	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.7	96.3		-1.4	96.3	10.0							
CRUSH – 2 FACE													

REMARKS Sampled at John C and Abbott at 11:00 AM

* CIRCLE TEST RESULTS OUT OF TOLERANCE