

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION 82000	JOB NUMBER 205935A/207914A	PROJECT LOCATION On Various Routes	MIX DESIGN NO 19MD411	MIXTURE TYPE 4E3	DATE SAMPLED 06/11/20	DATE TESTED 07/07/20
CONTRACTOR AJAX Paving Industries, Inc.			PLANT NUMBER 020-10	PLANT LOCATION Warren		SUBLOT SIZE
PROJECT ENGINEER Richard T. Doherty		NAME OF TESTER (Please Print) Brian Gondek		QUALIFICATION NO. 383-0421	LOT NUMBER 14	SUB LOT NUMBER 1 AM
Gb 1.029	Gsb 2.707	Gse 2.752	NAME OF TESTER (Signature) Brian J. Gondek Aug 6 2020 8:07 AM		FORM 1911 DATE 04/14/20	SUBLOT RANDOM TONS 100.00
ACCUMULATED TONS						

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5	ASPHALT %	5.15	5.05		-0.10	5.05	+0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5	Gmm	2.534	2.540		0.006	2.540	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5	Gmb @ N DESIGN	2.445					
P ½" (12.5 mm)	99.40	98.83		-0.57	98.83	5	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	84.00	88.56		4.56	88.56	5	VMA	14.34					
P No. 4 (4.75 mm)	61.60	64.50		2.90	64.50	5	VFA	75.58					
P No. 8 (2.36 mm)	45.60	45.98		0.38	45.98	5	F/A RATIO	1.21					
P No. 16 (1.18 mm)	34.00	39.88		5.88	39.88		Gse						
P No. 30 (600 µm)	26.50	24.95		-1.55	24.95	4		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	14.20	15.24		1.04	15.24		ASPHALT BINDER			Ajax Asphalt Terminal			3.80
P No. 100 (150 µm)	8.50	8.42		-0.08	8.42		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	5.50	6.43		0.93	6.43	1	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.0	97.9		0.9	97.9	10							
CRUSH – 2 FACE													

REMARKS Sampled at Lafayette and Meldrum @ 7:30AM

* CIRCLE TEST RESULTS OUT OF TOLERANCE