

[Clear Form](#)

Michigan Department
of Transportation
1903B (04/20)

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, **COPIES** – QA Laboratory, TMI, and Lansing C & T

File 208

CONTROL SECTION 82000	JOB NUMBER 205935A/207914A	PROJECT LOCATION On Various Routes	MIX DESIGN NO 19MD411	MIXTURE TYPE 4E3	DATE SAMPLED 06/12/20	DATE TESTED 07/08/20
CONTRACTOR AJAX Paving Industries, Inc.			PLANT NUMBER 020-10	PLANT LOCATION Warren		SUBLOT SIZE
PROJECT ENGINEER Richard T. Doherty		NAME OF TESTER <i>(Please Print)</i> Brian Gondek		QUALIFICATION NO. 383-0421	LOT NUMBER 15	SUB LOT NUMBER 1 AM
Gb 1.029	Gsb 2.707	Gse 2.752	NAME OF TESTER <i>(Signature)</i> Brian J. Gondek Aug 6 2020 8:11 AM		FORM 1911 DATE 04/14/20	SUBLOT RANDOM TONS 202.00
						ACCUMULATED TONS

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5	ASPHALT %	5.15	5.15		0.00	5.15	+0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5	Gmm	2.534	2.542		0.008	2.542	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5	Gmb @ N DESIGN	2.445					
P ½" (12.5 mm)	99.40	97.33		-2.07	97.33	5	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	84.00	87.92		3.92	87.92	5	VMA	14.34					
P No. 4 (4.75 mm)	61.60	64.15		2.55	64.15	5	VFA	75.58					
P No. 8 (2.36 mm)	45.60	47.00		1.40	47.00	5	F/A RATIO	1.21					
P No. 16 (1.18 mm)	34.00	35.99		1.99	35.99		Gse						
P No. 30 (600 µm)	26.50	24.39		-2.11	24.39	4		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	14.20	12.33		-1.87	12.33		ASPHALT BINDER			Ajax Asphalt Terminal			3.80
P No. 100 (150 µm)	8.50	7.29		-1.21	7.29		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	5.50	5.43		-0.07	5.43	1	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.0	96.9		-0.1	96.9	10							
CRUSH – 2 FACE													

REMARKS Sampled at Lafayette & Parker @ 9:00 AM

* CIRCLE TEST RESULTS OUT OF TOLERANCE