

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION 82000	JOB NUMBER 205935A/207914A	PROJECT LOCATION On Various Routes	MIX DESIGN NO 19MD411	MIXTURE TYPE 4E3	DATE SAMPLED 08/10/20	DATE TESTED 09/01/20
CONTRACTOR AJAX Paving Industries, Inc.			PLANT NUMBER 020-10	PLANT LOCATION Warren		SUBLOT SIZE
PROJECT ENGINEER Richard T. Doherty		NAME OF TESTER (Please Print) Brian Gondek		QUALIFICATION NO. 383-0421	LOT NUMBER 23	SUB LOT NUMBER 1 AM
Gb 1.029	Gsb 2.707	Gse 2.752	NAME OF TESTER (Signature) Brian J. Gondek Sep 24 2020 9:18 AM		FORM 1911 DATE 04/14/20	SUBLOT RANDOM TONS 533.00
ACCUMULATED TONS						

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5.0	ASPHALT %	5.15	5.35		0.20	5.35	0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmm	2.534	2.536		0.002	2.536	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmb @ N DESIGN	2.445					
P ½" (12.5 mm)	99.40	96.05		-3.35	96.05	5.0	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	84.00	85.78		1.78	85.78	5.0	VMA	14.34					
P No. 4 (4.75 mm)	61.60	63.65		2.05	63.65	5.0	VFA	75.58					
P No. 8 (2.36 mm)	45.60	46.76		1.16	46.76	5.0	F/A RATIO	1.21					
P No. 16 (1.18 mm)	34.00	35.79		1.79	35.79		Gse						
P No. 30 (600 µm)	26.50	23.23		-3.27	23.23	4.0		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	14.20	12.81		-1.39	12.81		ASPHALT BINDER						3.79
P No. 100 (150 µm)	8.50	7.36		-1.14	7.36		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	5.50	5.43		-0.07	5.43	1.0	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.0	97.9		0.9	97.9	10.0							
CRUSH – 2 FACE													

REMARKS Sampled at Bagley & Vermont @ 10:05 AM

* CIRCLE TEST RESULTS OUT OF TOLERANCE