

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION 82000		JOB NUMBER 205935A/207914A		PROJECT LOCATION On Various Routes		MIX DESIGN NO 19MD411		MIXTURE TYPE 4E3		DATE SAMPLED 08/11/20		DATE TESTED 09/01/20			
CONTRACTOR AJAX Paving Industries, Inc.						PLANT NUMBER 020-10		PLANT LOCATION Warren				SUBLOT SIZE			
PROJECT ENGINEER Richard T. Doherty				NAME OF TESTER <i>(Please Print)</i> Brian Gondek				QUALIFICATION NO. 383-0421		LOT NUMBER 24		SUB LOT NUMBER 2 PM			
Gb 1.029		Gsb 2.707		Gse 2.752		NAME OF TESTER <i>(Signature)</i> Brian J. Gondek Brian J. Gondek Sep 24 2020 9:21 AM				FORM 1911 DATE 04/14/20		SUBLOT RANDOM TONS 767.00		ACCUMULATED TONS	

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5.0	ASPHALT %	5.15	5.04		-0.11	5.04	0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmm	2.534	2.543		0.009	2.543	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmb @ N DESIGN	2.445					
P ½" (12.5 mm)	99.40	98.72		-0.68	98.72	5.0	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	84.00	88.47		4.47	88.47	5.0	VMA	14.34					
P No. 4 (4.75 mm)	61.60	64.64		3.04	64.64	5.0	VFA	75.58					
P No. 8 (2.36 mm)	45.60	47.74		2.14	47.74	5.0	F/A RATIO	1.21					
P No. 16 (1.18 mm)	34.00	35.97		1.97	35.97		Gse						
P No. 30 (600 µm)	26.50	25.71		-0.79	25.71	4.0		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	14.20	17.13		2.93	17.13		ASPHALT BINDER						3.79
P No. 100 (150 µm)	8.50	6.94		-1.56	6.94		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	5.50	4.94		-0.56	4.94	1.0	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.0	96.9		-0.1	96.9	10.0							
CRUSH – 2 FACE													

REMARKS Sampled at Bagley & St. Anne @ 12:05 PM

* CIRCLE TEST RESULTS OUT OF TOLERANCE