

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, **COPIES** – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION 82000	JOB NUMBER 205935A/207914A	PROJECT LOCATION On Various Routes	MIX DESIGN NO 19MD411	MIXTURE TYPE 4E3	DATE SAMPLED 09/01/20	DATE TESTED 09/24/20
CONTRACTOR AJAX Paving Industries, Inc.			PLANT NUMBER 020-10	PLANT LOCATION Warren		SUBLOT SIZE
PROJECT ENGINEER Richard T. Doherty		NAME OF TESTER <i>(Please Print)</i> Brian Gondek		QUALIFICATION NO. 383-0421	LOT NUMBER 28	SUB LOT NUMBER 1 AM
Gb 1.029	Gsb 2.707	Gse 2.752	NAME OF TESTER <i>(Signature)</i> Brian J. Gondek Dec 3 2020 3:29 PM		FORM 1911 DATE 04/14/20	ACCUMULATED TONS SUBLOT RANDOM TONS

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5.0	ASPHALT %	5.15	5.51		0.36	5.51	+0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmm	2.534	2.529		-0.005	2.529	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmb @ N DESIGN	2.445					
P ½" (12.5 mm)	99.40	97.30		-2.10	97.30	5.0	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	84.00	86.99		2.99	86.99	5.0	VMA	14.34					
P No. 4 (4.75 mm)	61.60	65.99		4.39	65.99	5.0	VFA	75.58					
P No. 8 (2.36 mm)	45.60	49.80		4.20	49.80	5.0	F/A RATIO	1.21					
P No. 16 (1.18 mm)	34.00	38.37		4.37	38.37		Gse						
P No. 30 (600 µm)	26.50	27.87		1.37	27.87	4.0		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	14.20	14.11		-0.09	14.11		ASPHALT BINDER						
P No. 100 (150 µm)	8.50	8.69		0.19	8.69		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	5.50	6.41		0.91	6.41	1.0	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.0	96.9		-0.1	96.9	10.0							
CRUSH – 2 FACE													

REMARKS Sampled @ 8:00 AM

* CIRCLE TEST RESULTS OUT OF TOLERANCE