

[Clear Form](#)

Michigan Department
of Transportation
1903B (04/20)

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, **COPIES** – QA Laboratory, TMI, and Lansing C & T

File 208

CONTROL SECTION 82000	JOB NUMBER 205935A	PROJECT LOCATION On Various Routes	MIX DESIGN NO 19MD411	MIXTURE TYPE 5E3	DATE SAMPLED 11/10/20	DATE TESTED 11/23/20
CONTRACTOR AJAX Paving Industries, Inc.			PLANT NUMBER 020-10	PLANT LOCATION Warren		SUBLOT SIZE
PROJECT ENGINEER Richard T. Doherty		NAME OF TESTER <i>(Please Print)</i> Brian Gondek		QUALIFICATION NO. 383-0421	LOT NUMBER 26	SUB LOT NUMBER 1 AM
Gb 1.029	Gsb 2.696	Gse 2.763	NAME OF TESTER <i>(Signature)</i> Brian J. Gondek Dec 3 2020 3:27 PM		FORM 1911 DATE 04/14/20	SUBLOT RANDOM TONS 251.00
ACCUMULATED TONS						

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5.0	ASPHALT %	6.15	5.87		-0.28	5.87	+0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmm	2.504	2.486		-0.018	2.486	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmb @ N DESIGN	2.416					
P ½" (12.5 mm)	100.00	100.00		0.00	100.00	5.0	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	99.50	99.35		-0.15	99.35	5.0	VMA	15.90					
P No. 4 (4.75 mm)	83.50	81.11		-2.39	81.11	5.0	VFA	77.99					
P No. 8 (2.36 mm)	62.20	63.60		1.40	63.60	5.0	F/A RATIO	1.17					
P No. 16 (1.18 mm)	46.40	50.90		4.50	50.90		Gse						
P No. 30 (600 µm)	34.80	34.61		-0.19	34.61	4.0		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	18.20	16.17		-2.03	16.17		ASPHALT BINDER	PG 58-28		Ajax Asphalt Terinal Detroit 2500			4.54
P No. 100 (150 µm)	10.20	9.31		-0.89	9.31		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	6.20	6.78		0.58	6.78	1.0	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.7	97.1		-0.6	97.1	10.0							
CRUSH – 2 FACE													

REMARKS Sampled at Tireman & M-39 Service Drive @ 8:40 AM

* CIRCLE TEST RESULTS OUT OF TOLERANCE