

Michigan Department
of Transportation
1903C (05/15)

DAILY REPORT OF CONTRACTORS QUALITY CONTROL TESTS

DISTRIBUTION: ORIGINAL - Project Engineer, COPIES -

CONTROL SECTION STU 82000		JOB NUMBER 205935A		PROJECT LOCATION Various Route In Detroit		MIX DESIGN NUMBER 19MD 140		MIXTURE TYPE 5E 3		DATE SAMPLED 11/10/2019		DATE TESTED 11/11/2019			
CONTRACTOR AJAX PAVING INDUSTRIES				PLANT No. 20-10		PLANT LOCATION 26400 SHERWOOD RD				Form 1911 DATE 9/30/2019					
PROJECT ENGINEER Richard T. Doherty				NAME OF TESTER(Please print) Jesus Soto Sancen				NAME OF TESTER (SIGNATURE) Jesus Sancen Digitally signed by Jesus Sancen Date: 2019.11.11 10:43:15 -05'00'				QUALIFICATION NUMBER 0664-0520			
GB 1.029		Gsb 2.696		Gse 2.763		SUBLOT SIZE 1000		LOT NO 2		SUBLOT NO 7		SUBLOT RANDOM TONS 450		ACCUMULATED TONS 0.00	

TEST RESULTS							TEST RESULTS						
	JMF	CONTR	DEV.	Range 1	Range 2	AGG.		JMF	CONTR	DEV.	Range 1	Range 2	
P 1 1/2" (37.5mm)	100.00%	100.00%	0.00%				ASPHALT %	6.15%	5.92%	-0.23%	+/- 0.50	+/- 0.75	
P 1" (25.0mm)	100.00%	100.00%	0.00%				Gmm	2.504			+/- 0.013	+/- 0.020	
P 3/4" (19.0mm)	100.00%	100.00%	0.00%				Gmb @ N DESIGN	2.416					
P 1/2" (12.5mm)	100.00%	100.00%	0.00%				AIR VOIDS	3.50%			+ 2.11 - 3.89	+/-2.10 3.90	
P 3/8" (9.5mm)	99.50%	99.52%	0.02%	+/- 8.00	+/- 10.00		VMA	15.90			+/-15.11 16.89	+/-15.10 16.90	
P No. 4 (4.75mm)	83.50%	83.89%	0.39%	+/- 6.00	+/- 8.00		VFA	77.99					
P No. 8 (2.36mm)	62.20%	65.46%	3.26%	+/- 6.00	+/- 8.00		F/A RATIO	1.17			+/-0.60 1.40	+/-0.60 1.40	
P No. 16 (1.18mm)	46.40%	50.89%	4.49%										
P No. 30 (600 Um)	34.80%	37.69%	2.89%	+/- 4.00	+/- 6.00								
P No. 50 (300 Um)	18.20%	19.70%	1.50%										
P No. 100 (150 Um)	10.20%	9.37%	-0.83%										
P No. 200 (75 Um)	6.20%	6.01%	-0.19%	+/- 1.00	+/- 2.00								
CRUSH - 1 FACE	97.70%	97.43%	-0.27%	+/- 10.00	+/- 15.00								
CRUSH - 2 FACE	0.00%	0.00%	0.00%										

	GRADE	Certified Supplier/Location/CERT#	% ADD
ASPHALT BINDER	PG 58-28	Ajax Asphalt Terminal Detroit	ABS.2500 4.55%
GYRATORY WEIGHTS/COMPACTION TEMPERATURE			
MARSHALL WEIGHTS/COMPACTION TEMPERATURE			
NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)			

REMARKS

*CIRCLE TEST RESULTS THAT ARE OUT OF LIMITS.