

Michigan Department
of Transportation
1903C (04/20)

DAILY REPORT OF CONTRACTOR'S QUALITY CONTROL TESTS

DISTRIBUTION: ORIGINAL - Project Engineer, COPIES - TMI

CONTROL SECTION STU 82000		JOB NUMBER 205935A		PROJECT LOCATION Various Route In Detroit		MIX DESIGN NUMBER 19MD 140		MIXTURE TYPE 5E 3		DATE SAMPLED 9/10/2020		DATE TESTED 9/11/2020	
CONTRACTOR AJAX PAVING INDUSTRIES				PLANT No. 20-10		PLANT LOCATION 26400 SHERWOOD RD				Form 1911 DATE 4/14/2020			
PROJECT ENGINEER Richard T. Doherty				NAME OF TESTER(Please print) Jesus Soto Sancen				NAME OF TESTER (SIGNATURE) Jesus Sancen Digitally signed by Jesus Sancen Date: 2020.09.11 10:52:31 -04'00'				QUALIFICATION NUMBER 0664-0423	
GB 1.029		Gsb 2.696		Gse 2.763		SUBLOT SIZE 1000		LOT NO 7		SUBLOT NO 31		SUBLOT RANDOM TONS 96.19	
												ACCUMULATED TONS 0.00	

TEST RESULTS

	JMF	CONTR	DEV.	Range 1	Range 2		AGG.
P 1 1/2" (37.5mm)	100.00%	100.00%	0.00%				
P 1" (25.0mm)	100.00%	100.00%	0.00%				
P 3/4" (19.0mm)	100.00%	100.00%	0.00%				
P 1/2" (12.5mm)	100.00%	99.47%	-0.53%				
P 3/8" (9.5mm)	99.50%	97.43%	-2.07%	+/- 8.00	+/-10.00		
P No. 4 (4.75mm)	83.50%	83.83%	0.33%	+/- 6.00	+/- 8.00		
P No. 8 (2.36mm)	62.20%	65.44%	3.24%	+/- 6.00	+/- 8.00		
P No. 16 (1.18mm)	46.40%	49.98%	3.58%				
P No. 30 (600 Um)	34.80%	36.41%	1.61%	+/- 4.00	+/- 6.00		
P No. 50 (300 Um)	18.20%	18.56%	0.36%				
P No. 100 (150 Um)	10.20%	9.71%	-0.49%				
P No. 200 (75 Um)	6.20%	6.81%	0.61%	+/- 1.00	+/- 2.00		
CRUSH - 1 FACE	97.70%	96.60%	-1.10%	+/-10.00	+/-15.00		
CRUSH - 2 FACE	0.00%	0.00%	0.00%				

TEST RESULTS

	JMF	CONTR	DEV.	Range 1		Range 2		
ASPHALT %	6.15%	6.23%	0.08%	+/-	0.50	+/-	0.75	
Gmm	2.504			+/-	0.013	+/-	0.020	
Gmb @ N DESIGN	2.416							
AIR VOIDS	3.50%			+	2.11	- 3.89	+/- 2.10	3.90
VMA	15.90			+/-	15.11	16.89	+/- 15.10	16.90
VFA	77.99							
F/A RATIO	1.17			+/-0.60	1.40	+/-0.60	1.40	
Gse	2.763			+/-		+/-		
		GRADE		Certified Supplier/Location/CERT#				% ADD
ASPHALT BINDER		PG 58-28		Ajax Asphalt Terminal DetroitABS.2500				4.55%
GYRATORY WEIGHTS/COMPACTION TEMPERATURE								
MARSHALL WEIGHTS/COMPACTION TEMPERATURE								
NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)								

REMARKS

*CIRCLE TEST RESULTS THAT ARE OUT OF LIMITS.