

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION N/A		JOB NUMBER PW-7018		PROJECT LOCATION HMA Mill & Resurfacing 2020 Major Roads		MIX DESIGN NO 19MD140		MIXTURE TYPE 5E3		DATE SAMPLED 09/15/20		DATE TESTED 09/30/20	
CONTRACTOR AJAX Paving Industries, Inc.						PLANT NUMBER 020-10		PLANT LOCATION Warren				SUBLOT SIZE	
PROJECT ENGINEER Jason Lukasik, P.E.				NAME OF TESTER (Please Print) Brian Gondek				QUALIFICATION NO. 383-0421		LOT NUMBER 11		SUB LOT NUMBER 1 AM	
Gb 1.029		Gsb 2.696		Gse 2.763		NAME OF TESTER (Signature) Brian J. Gondek Oct 30 2020 12:45 PM				FORM 1911 DATE 04/14/20		SUBLOT RANDOM TONS 351.00	

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5.0	ASPHALT %	6.15	6.59		0.44	6.59	0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmm	2.504	2.501		-0.003	2.501	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmb @ N DESIGN	2.416					
P ½" (12.5 mm)	100.00	100.00		0.00	100.00	5.0	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	99.50	95.04		-4.46	95.04	5.0	VMA	15.90					
P No. 4 (4.75 mm)	83.50	80.25		-3.25	80.25	5.0	VFA	78.00					
P No. 8 (2.36 mm)	62.20	60.89		-1.31	60.89	5.0	F/A RATIO	1.17					
P No. 16 (1.18 mm)	46.40	47.19		0.79	47.19		Gse						
P No. 30 (600 µm)	34.80	32.48		-2.32	32.48	4.0		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#			% ADD
P No. 50 (300 µm)	18.20	16.85		-1.35	16.85		ASPHALT BINDER	PG 58-28		Ajax Asphalt Terminal			4.54
P No. 100 (150 µm)	10.20	8.88		-1.32	8.88		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	6.20	6.42		0.22	6.42	1.0	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.7	97.5		-0.2	97.5	10.0							
CRUSH – 2 FACE													

REMARKS Sampled at Tireman & Stahelin @ 8:00 AM

* CIRCLE TEST RESULTS OUT OF TOLERANCE