

REPORT OF QUALITY ASSURANCE TESTING

DISTRIBUTION: ORIGINAL – Project Engineer, COPIES – QA Laboratory, TMI, and Lansing C & T

CONTROL SECTION N/A	JOB NUMBER PW-7018	PROJECT LOCATION HMA Mill & Resurfacing 2020 Major Roads	MIX DESIGN NO 19MD140	MIXTURE TYPE 5E3	DATE SAMPLED 11/20/20	DATE TESTED 12/01/20
CONTRACTOR AJAX Paving Industries, Inc.			PLANT NUMBER 020-10	PLANT LOCATION Warren		SUBLOT SIZE
PROJECT ENGINEER Jason Lukasik, P.E.		NAME OF TESTER (Please Print) Brian Gondek		QUALIFICATION NO. 383-0421	LOT NUMBER 15	SUB LOT NUMBER 2 PM
Gb 1.029	Gsb 2.696	Gse 2.763	NAME OF TESTER (Signature) Brian J. Gondek Dec 4 2020 9:29 AM		FORM 1911 DATE 04/14/20	ACCUMULATED TONS

TEST RESULTS							TEST RESULTS						
	JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL		JMF	MDOT	CONTR	MDOT DIFF. JMF *	MDOT DIFF. CONTR *	TOL
P 1-½" (37.5 mm)	100.00	100.00		0.00	100.00	5.0	ASPHALT %	6.15	5.86		-0.29	5.86	0.40/-0.30
P 1" (25.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmm	2.504	2.498		-0.006	2.498	
P ¾" (19.0 mm)	100.00	100.00		0.00	100.00	5.0	Gmb @ N DESIGN	2.416					
P ½" (12.5 mm)	100.00	100.00		0.00	100.00	5.0	AIR VOIDS	3.50					
P 3/8" (9.5 mm)	99.50	99.24		-0.26	99.24	5.0	VMA	15.90					
P No. 4 (4.75 mm)	83.50	83.23		-0.27	83.23	5.0	VFA	78.00					
P No. 8 (2.36 mm)	62.20	61.45		-0.75	61.45	5.0	F/A RATIO	1.17					
P No. 16 (1.18 mm)	46.40	45.92		-0.48	45.92		Gse						
P No. 30 (600 µm)	34.80	30.97		-3.83	30.97	4.0		GRADE		CERTIFIED SUPPLIER / LOCATION/CERT#		% ADD	
P No. 50 (300 µm)	18.20	17.95		-0.25	17.95		ASPHALT BINDER	PG 58-28		Ajax Asphalt Terminal		4.54	
P No. 100 (150 µm)	10.20	9.48		-0.72	9.48		Gmb WEIGHTS/COMPACTION TEMPERATURE						
P No. 200 (75 µm)	6.20	6.93		0.73	6.93	1.0	NUMBER OF SOLVENT WASHES (When using the vacuum extraction method for Asphalt %)						
CRUSH – 1 FACE	97.7	97.6		-0.1	97.6	10.0							
CRUSH – 2 FACE													

REMARKS Sampled at East Grand near Windmere @ 12:40 PM

* CIRCLE TEST RESULTS OUT OF TOLERANCE